

# Technical Data Sheet



Tradition 4V WR


















Class 33 according to EN 13329

Version: 04/2024


**Profile:**

**megaloc**  
aqua protect

**Core board:** Classenboard HDF  
**Dimensions:** 1285 x 192 x 8 mm  
**Quantity / Weight per box (PU):** 9 pieces = 2.220 m<sup>2</sup> / approx. 15 kg  
**Quantity / Weight per pallet:** 44 PU = 97.70 m<sup>2</sup> / approx. 691 kg

Characteristics	Test Method	Requirements
<b>General Requirements</b>		
Geometrical characteristics	EN 17539	Length: ± 0.5 mm Width: ± 0.1 mm
Thickness	EN 17539	± 0.5 mm
Squareness	EN 17539	max. ≤ 0.20 mm
Straightness	EN 17539	max. ≤ 0.30 mm/m
Flatness of the elements	EN 17539	Width: concave ≤ 0.15%, convex ≤ 0.20 % Length: concave ≤ 0.50 %, convex ≤ 1.00 %
Openings	EN 17539	Ø ≤ 0.15 mm max. ≤ 0.20 mm
Height difference	EN 17539	Ø ≤ 0.10 mm max. ≤ 0.15 mm
Residual indentation	 EN ISO 24343-1	≤ 0.05 mm
Light fastness	 EN ISO 4892-2	grey scale level ≥ 4
<b>Classification Requirements</b>		
Wear resistance	 ISO 24338 method A	≥ 6000 cycles ( AC5 )
Impact resistance	 EN 17368 EN 13329 Annex C	small - diameter ball ≥ 70 mm large - diameter ball ≥ 750 mm
Castor chair resistance	 ISO 4918	no damage with type W after 20 000 cycles
Thickness swelling	 ISO 24336	≤ 15 %
Locking strength	 ISO 24334	F <sub>0.2</sub> ≥ 1.0 kN/m F <sub>s0.2</sub> ≥ 2.0 kN/m
Movement of a furniture leg	 EN ISO 16581	no damage with type 0
Resistance to staining	 EN 438-2	5 (group 1 and 2), 4 ( group 3)
Surface soundness	EN 13329	≥ 1.25 N/mm <sup>2</sup>
<b>Essential Characteristics</b>		
Reaction to fire*	 EN 13501-1	C <sub>fl</sub> - s1
Slip resistance*	 EN 16165	DS
Electrostatic behavior*	 EN 1815	≤ 2 kV
Formaldehyde*	 EN 16516	E1
Formaldehyde-Emissions	ASTM D6007	US EPA TSCA Title VI / CARB P 2
Thermal conductivity*	 EN 12667	≥ 0.075 W/mK
Thermal resistance*	 EN 12667	R ≤ 0.07 (m <sup>2</sup> K)/W
<b>Additional requirements</b>		
Topical moisture resistance-surface swell	ISO 4760	- Qualitative recovery swell rating final average < 3 - Recovery swell final average ≤ 0.3 mm swelling
Topical moisture resistance-water tightness of the joints	ISO 4760	No water leakage through the joints after 48 hours exposure to water
VOC Emissions	  <a href="http://www.blauer-engel.de/uz176">www.blauer-engel.de/uz176</a> • emissions- und schadstoffarm • Holz aus nachhaltiger Forstwirtschaft • in der Wohnumwelt gesundheitlich unbedenklich	 
Sustainability		

We guarantee consistency of our decor colours under artificial light of type D50 (CIE D50, ANSI PH 2.30, ISO 3664) and D65 (CIE D65).

\* basic attributes concerning health, safety and energy saving acc. to  EN 14041

Our technical data sheets are constantly updated and adapted to the state of the art.

This edition replaces all previous versions and is valid at the time of writing.

This document is valid without signature.